

DATA SHEET

E101

+	Electrical Resistivity $\mu\Omega\text{m}$	40
+	Flexural Strenght N/mm^2	30
+	* Current Density A/cm^2	4.0 – 16.0
+	Rockwell Hardness HR 10/40	95
+	Peripheral Speed m/s	50
+	Voltage Drop V	1.4 ÷ 2.6
+	Bulk Density g/cm^3	1.60
+	Coefficient of Friction	0.06 - 0.11

* Peak Current Density 20.0A/cm^2



Via Casale, 7/A
03100 Frosinone (FR)
ITALIA

+39 0775 25 71 65

✉ commerciale@cetec.it

www.cetecspa.it