

mica tapes

Samicaflex® 366.19

- For RR and VPI impregnation
- High thermal stability
- Extreme flexibility
- For class H & C applications

		Value	Test norm
Thickness	mm	0.18 ± 0.03	IEC 60371-2
Total weight	mm	215 ± 18	IEC 60371-2
Mica paper	g/m ²	120 ± 6	IEC 60371-2
Glass fabric	g/m ²	23 ± 2	IEC 60371-2
Resin content	g/m ²	72 ± 10	IEC 60371-2
Tensile strength	N	≥80	IEC 60371-2
Stiffness	N/m	≤55	IEC 60371-2
Breakdown voltage	kV	≥2.6	IEC 60371-2
Min. shelf life at 20°C		12 months	
Min. shelf life at 5°C		24 months	

General description

Samicaflex® 366.19 is based upon a woven glass fabric with an impregnated muscovite micapaper.

Application

Samicaflex® 366.19 is recommended for all motor applications up to 220°C, where retained flexibility is necessary. It is used in traction motors for both armature coils and field coils. Samicaflex® might also be used as overhang insulation in class F Resin Rich processed high voltage coils. Samicaflex® is also used as thermal and electrical insulation on induction furnace coils up to the highest temperatures.

Form of delivery

Samicaflex® 366.19 tapes are usually delivered in widths from 10mm on. Our range of cores satisfies the needs of manual and mechanical processing.

Main characteristics

Samicaflex® 366.19 is a "B" stage material with excellent electrical properties at very high temperatures and with exceptional retained flexibility after prolonged exposure to high temperature.

Processing

We recommend to apply these tapes half lapped with the woven glass to the outside.

Samicaflex® 366.19 must be fully cured after application, when used as overhang insulation of machines which are to be vacuum pressure impregnated (VPI).

Health and safety

While processing Samicaflex® 366.19 we recommend to follow all hygiene and safety standards.

The product properties set forth in this data sheet are based on the results of testing of typical material produced by the affiliated companies of Von Roll Holding Ltd. (underneath referred as Von Roll). Some variation in product properties is typical. Comments or suggestions relating to any subject other than product properties are offered only to call the end-user's or other person's attention to considerations which may be relevant in the independent determination of the use and/or manner of use of product. Von Roll does not claim or warrant that the use of its product will have the results described in this data sheet or that the information provided is complete, accurate or useful. The user should test the product to determine its properties and its suitability for the intended use. Von Roll expressly disclaims any liability for any damage, harm, injury, cost or expense to any person resulting directly or indirectly from that person's reliance on any information contained in this data sheet. Nothing contained in this data sheet constitutes representation or warranty as to any matter whatsoever. Von Roll makes no warranties whatsoever in this data sheet, expressed or implied, including any implied warranty or fitness for a particular use or purpose. Von Roll shall in no event be liable for incidental, exemplary, punitive or consequential damages.